# productinformation

## tesa<sup>®</sup> 51972 48μm double sided black filmic tape

tesa® 51972 is a double-sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

tesa® 51972 features especially:

- Thickness: 48µm
- High adhesion level
- Excellent resistance to demanding environmental conditions
- Excellent handling performance in converting processes

#### Main Application

- Mounting of metal or plastic badges and signs
- Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

#### Technical Data

<ul><li>Backing material</li><li>Color</li><li>Total thickness</li></ul>	PET film black 48 μm	<ul><li>Type of adhesive</li><li>Elongation at break</li><li>Tensile strength</li></ul>	tackified acrylic 50 % 20 N/cm
Adhesion to			
<ul> <li>Steel (initial)</li> <li>ABS (initial)</li> <li>Aluminium (initial)</li> <li>PC (initial)</li> <li>PE (initial)</li> <li>PET (initial)</li> <li>PP (initial)</li> <li>PS (initial)</li> </ul>	7.0 N/cm 5.3 N/cm 5.2 N/cm 6.5 N/cm 3.1 N/cm 5.3 N/cm 3.0 N/cm 5.4 N/cm	<ul> <li>Steel (after 14 days)</li> <li>ABS (after 14 days)</li> <li>Aluminium (after 14 days)</li> <li>PC (after 14 days)</li> <li>PE (after 14 days)</li> <li>PET (after 14 days)</li> <li>PP (after 14 days)</li> <li>PS (after 14 days)</li> </ul>	9.6 N/cm 6.5 N/cm 7.7 N/cm 8.6 N/cm 3.5 N/cm 7.0 N/cm 4.8 N/cm 7.1 N/cm

#### Properties

<ul><li>Temperature resistance long term</li><li>Tack</li></ul>	200 °C 100 °C	<ul> <li>Resistance to chemicals</li> <li>Softener resistance</li> <li>Static shear resistance at 23°C</li> </ul>	• • • • • •
<ul><li>Ageing resistance (UV)</li><li>Humidity resistance</li></ul>	••••	<ul> <li>Static shear resistance at 40°C</li> </ul>	••
Evaluation across relevant tesa <sup>®</sup> assortment:	•••• verv good	🗨 🗨 good 🛛 🗨 medium 🔍 low	

#### For latest information on this product please visit <u>http://l.tesa.com/?ip=51972</u>

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



great to work with

## tesa<sup>®</sup> 51972 48μm double sided black filmic tape

### Additional Information

Liner variants: PV20 brown/blue logo glassine paper (71µm; 82g/m<sup>2</sup>)

For latest information on this product please visit <u>http://l.tesa.com/?ip=51972</u>

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

