# productinformation

# tesa® 68740

# 30µm double sided black filmic tape

tesa® 68740 is a black, double-sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

tesa® 68740 features esp.

- Thickness: 30μm
- Good adhesion level
- Excellent resistance to demanding environmental conditions
- Excellent handling performance in converting processes

# Main Application

- Lamination of cushioning materials to LCDs
- Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

#### Technical Data

	Backing material	PET film		Type of adhesive	tackified acrylic
	Color	black		Elongation at break	50 %
•	Total thickness	30 μm	•	Tensile strength	20 N/cm

# Adhesion to

<ul> <li>Steel (initial)</li> <li>4.5 N/cm</li> <li>Steel (after 14 days)</li> </ul>	5.9 N/cm
<ul> <li>ABS (initial)</li> <li>4.4 N/cm</li> <li>ABS (after 14 days)</li> </ul>	5.8 N/cm
<ul> <li>Aluminium (initial)</li> <li>3.9 N/cm</li> <li>Aluminium (after 14 days)</li> </ul>	5.3 N/cm
<ul> <li>PC (initial)</li> <li>5.3 N/cm</li> <li>PC (after 14 days)</li> </ul>	6.5 N/cm
<ul> <li>PE (initial)</li> <li>1.5 N/cm</li> <li>PE (after 14 days)</li> </ul>	2.0 N/cm
<ul> <li>PET (initial)</li> <li>3.8 N/cm</li> <li>PET (after 14 days)</li> </ul>	5.2 N/cm
<ul><li>PP (initial)</li><li>1.4 N/cm</li><li>PP (after 14 days)</li></ul>	2.8 N/cm
<ul> <li>PS (initial)</li> <li>3.4 N/cm</li> <li>PS (after 14 days)</li> </ul>	5.0 N/cm
<ul> <li>PVC (initial)</li> <li>4.1 N/cm</li> <li>PVC (after 14 days)</li> </ul>	7.3 N/cm

# **Properties**

•	Temperature resistance short term	200 °C		Resistance to chemicals	•••
	Temperature resistance long term	100 °C		Softener resistance	• • •
	Tack	•		Static shear resistance at 23°C	••••
	Ageing resistance (UV)	•••		Static shear resistance at 40°C	•••
٠	Humidity resistance	•••			
Ev	aluation across relevant tesa® assortment	: ••• very good	•	● good ● ● medium ● low	

For latest information on this product please visit http://l.tesa.com/?ip=68740

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 1 of 2 - as of 06/07/2018 - ensg

# tesa® 68740 30µm double sided black filmic tape

# Additional Information

Liner variants:

PV20 brown/blue logo glassine paper (71μm; 82g/m²)