



# tesa<sup>®</sup> 75743

## 제품 정보

200µm d/s white reinforced acrylic foam tape

## 제품 설명

tesa<sup>®</sup> 75743 is a double-sided white tape with PET backing. The tape is equipped with a novel foamed shock and anti-repulsion adhesive.

tesa<sup>®</sup> 75743 features:

- \* Thickness: 200µm
- \* Very high shock performance
- \* Very high thermal shock resistance
- \* Very high bonding strength
- \* Good anti-repulsion properties to prevent lifting
- \* Good reworkability and die-cut ability
- \* Waterproofing

## 특성

- Thickness: 200µm
- \* Very high shock performance
- \* Very high thermal shock resistance
- \* Very high bonding strength
- \* Good anti-repulsion properties to prevent lifting
- \* Good reworkability and die-cut ability
- \* Waterproofing

## Applications

- Demanding touch panel, lens or screen mounting applications with high requirements for impact resistance
- \* Mounting of Displays

최신정보는 왼쪽 링크를 클릭하세요. <http://l.tesa.com/?ip=75743>



# tesa<sup>®</sup> 75743

## 제품 정보

### Applications

- \* Mounting of ultra slim bezel designs
- \* Mounting of waterproof designs

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### 제품 구조

|          |        |          |                     |
|----------|--------|----------|---------------------|
| • 기재 소재  | PETP   | • 컬러     | white               |
| • 점착제 종류 | 변성 아크릴 | • 이형지 두께 | 50 µm               |
| • 이형지 종류 | PET    | • 이형지 무게 | 72 g/m <sup>2</sup> |
| • 총두께    | 200 µm | • 이형지 색깔 | 투명성                 |

### 속성 / 성능 값

|            |           |                  |       |
|------------|-----------|------------------|-------|
| • 연신률      | 100 %     | • 장기간 온도저항       | 80 °C |
| • 노후성 (UV) | very good | • 정적 전단응력 (23°C) | good  |
| • 단기간 온도저항 | 130 °C    | • 정적 전단응력 (40°C) | good  |

### 점착력

|                 |           |                    |          |
|-----------------|-----------|--------------------|----------|
| • 유리점착력 (초기)    | 12.5 N/cm | • PE점착력 (초기)       | 7.5 N/cm |
| • 유리점착력 (3일 경과) | 13 N/cm   | • PE점착력 (3일 경과)    | 8.5 N/cm |
| • PC점착력 (초기)    | 12 N/cm   | • Steel점착력 (초기)    | 14 N/cm  |
| • PC점착력 (3일 경과) | 13.5 N/cm | • Steel점착력 (3일 경과) | 15 N/cm  |

### 면책사항

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타 문의사항이 있으시면 저희 직원에게 문의 바랍니다



최신정보는 왼쪽 링크를 클릭하세요. <http://l.tesa.com/?ip=75743>