



tesa® 61564

제품 정보

75µm moisture control transparent transfer tape

제품 설명

tesa® 61564 is a highly transparent transfer tape produced under controlled clean room conditions and designed for optically clear lamination which needs additional moisture control

특성

- Low WVTR provides moisture control
- Low dielectric constant
- High transmission and low haze
- Excellent temperature, humidity and UV resistance
- Excellent ITO compatibility
- High bonding strength
- Smooth and easy liner removal

Applications

- Lamination of films to rigid or flexible substrates
- Bonding of sensitive films, displays or touch panel

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

제품 구조

- | | | | |
|----------|-------|-----------------|--------|
| • 기재 소재 | 없음 | • 컬러 | 투명성 |
| • 접착제 종류 | 특수 | • 이형력 낮은 이형지 두께 | 50 µm |
| • 이형지 종류 | PET | • 이형력 높은 이형지 두께 | 100 µm |
| • 총두께 | 75 µm | • 이형지 색깔 | 투명성 |

속성 / 성능 값

- | | | | |
|----------------------|------------|----------------------|-------|
| • WVTR (38°C, 90%RH) | 17 g/sqm*d | • 투과성(380 - 780nm) > | 99 % |
| • 굴절율 | 1.52 | • 헤이즈 < | 0.5 % |

접착력(수치)

- | | | | |
|--------------|----------|----------------|----------|
| • 유리접착력 (초기) | 5.2 N/cm | • PET접착력 (초기) | 3.5 N/cm |
| • PC접착력 (초기) | 5 N/cm | • PMMA접착력 (초기) | 5.4 N/cm |



tesa® 61564

제품 정보

추가정보

- Easy release liner outside of roll

공지사항

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타 문의사항이 있으시면 저희 직원에게 문의 바랍니다



관련제품 최신자료는 다음의 경로를 클릭하세요 <http://l.tesa.com/?ip=61564>