

# tesa<sup>®</sup> 58346

## 제품정보



90 µm single-sided transparent PET filmic tape.

## 제품 설명

The tackified acrylic adhesive gives this product outstanding removability without residue while using for temporary protection on surface. The 75 µm transparent PET filmic backing offers excellent electrical insulation property. The PET liner ensures it can be easily released without adhesive residue.

## 특성

- Easy removal without adhesive residue.
- Excellent electrical insulation property when it applies on surface with dielectric strength 132.1kV/mm.
- Easy for converting and die-cutting.

## Applications

- Electrical insulation with removability for temporary protection.

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## 제품 구조

|          |        |          |       |
|----------|--------|----------|-------|
| • 기재 소재  | PET필름  | • 총두께    | 90 µm |
| • 점착제 종류 | 변성 아크릴 | • 컬러     | 투명성   |
| • 이형지 종류 | PET필름  | • 이형지 두께 | 36 µm |

## 속성 / 성능 값

|            |           |            |         |
|------------|-----------|------------|---------|
| • 연신률      | 140 %     | • 떼어내기 쉬운  | 네       |
| • 내습성      | very good | • 장기간 온도저항 | 125 °C  |
| • 내화학성     | medium    | • 절연파괴전압   | 12000 V |
| • 다이컷팅에 적합 | 네         |            |         |

## 점착력

|                |           |                 |           |
|----------------|-----------|-----------------|-----------|
| • 알루미늄점착력 (초기) | 0.16 N/cm | • Steel점착력 (초기) | 0.22 N/cm |
|----------------|-----------|-----------------|-----------|

# tesa® 58346

## 제품정보

### 면책사항

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타 문의사항이 있으시면 저희 직원에게 문의 바랍니다



최신정보는 왼쪽 링크를 클릭하세요. <http://l.tesa.com/?ip=58346>