



# tesa® 4976

## 제품 정보



540 µm double sided PU foam tape

## 제품 설명

tesa® 4976 is a double sided tape consisting of a conformable black open cell PU foam backing and a tackified acrylic adhesive.

## 특성

- Good compensation for design tolerances
- Level out different thermal elongation of materials
- Shock absorption and sealing function
- High short term temperature resistance

## Applications

- Fixing of mirrors, decorative profiles and signs
- Mounting of cable channels

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## 제품 구조

• 기재 소재	PU 폼	• 컬러	검정
• 점착제 종류	변성 아크릴, 아크릴, 개선된 아크릴	• 이형지 두께	70 µm
• 이형지 종류	글라신지	• 이형지 무게	80 g/m <sup>2</sup>
• 총두께	540 µm		

## 속성 / 성능 값

• 연신률	250 %	• 단기간 온도저항	200 °C
• 인장강도	6.66 N/cm	• 장기기간 온도저항	80 °C
• Tack	good	• 정적 전단응력 (23°C)	good
• 내화학성	medium, good	• 정적 전단응력 (40°C)	good
• 노후성 (UV)	medium, good		



# tesa<sup>®</sup> 4976

## 제품 정보

### 접착력(수치)

• ABS접착력 (초기)	7 N/cm	• PET접착력 (14일 경과)	10 N/cm
• ABS접착력 (14일 경과)	12 N/cm	• PP접착력 (초기)	3.7 N/cm
• 알루미늄접착력 (초기)	5 N/cm	• PP접착력 (14일 경과)	7.4 N/cm
• 알루미늄접착력 (14일 경과)	9 N/cm	• PS접착력 (초기)	5 N/cm
• PC접착력 (초기)	8 N/cm	• PS접착력 (14일 경과)	10 N/cm
• PC접착력 (14일 경과)	12 N/cm	• PVC접착력 (초기)	5.5 N/cm
• PE접착력 (초기)	4.1 N/cm	• PVC접착력 (14일 경과)	12 N/cm
• PE접착력 (14일 경과)	4.3 N/cm	• Steel접착력 (초기)	10 N/cm
• PET접착력 (초기)	5.5 N/cm	• Steel접착력 (14일 경과)	12 N/cm

### 추가정보

Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

### 공지사항

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타 문의 사항이 있으시면 저희 직원에게 문의 바랍니다



관련제품 최신자료는 다음의 경로를 클릭하세요 <http://l.tesa.com/?ip=04976>