

# tesa® 60151 Adhesion Promoter Glass



## 제품 정보

### 유리용 접착 촉진제

tesa® Adhesion Promoter는 tesa® ACX<sup>plus</sup> 테이프의 유리 접착력을 강화시키는 데에 사용되는 제품입니다.

### 주 용도

유리 전용. 광택 처리나 호일 코팅된 유리에는 사용을 권장하지 않음.  
부착력 향상 및 유리의 습기 방지에 사용됨

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### 물성자료

• 색깔	투명성	• 점도	2.5 mPa s
• 일관성	액체	• 밀도	0.81 g/cm <sup>3</sup>
• 고형물	0.5 %	• 확산속도	15 m <sup>2</sup> /l

#### 추가정보

Before using our adhesion promoter, the bonding surface, i.e. the substrate, should be free of dust, grease, oil, moisture, and other contaminants. Therefore, we highly recommend cleaning the substrate with a lint-free cloth using solvents, such as ethanol or isopropanol alcohol or our tesa® 60040 Industry Cleaner.

Once the surface has been cleaned, you can go ahead and apply our tesa® 60151 Adhesion Promoter. We recommend applying our adhesion promoters with a lint-free cloth, brush or sponge. Wet the cloth thoroughly with tesa® Adhesion Promoter and wipe once and in a single direction over the surface. Immediately use another lint-free cloth to remove excess adhesion promoter from the surface- a squeaking noise indicates a good layer thickness on most glass types. The entire surface should be coated thinly with adhesion promoter in order to reach the highest bonding performance. It is important to wait at least 30 seconds (and a maximum of 5 minutes) in order to give solvents time to evaporate. Please make sure to keep the prepared surface free of contaminants prior to applying the tape.

Once the substrate has been properly pre-treated with tesa® 60151 Adhesion Promoter, the bond should be established within 15 minutes. Please note that due to the multitude of available substrate formulations in the marketplace, it is recommended to test our tesa® Adhesion Promoter prior to usage.

- The shelf life of this product amounts to at least 12 months when stored at room temperature in its sealed original container.
- For further information and advice on safe handling please refer to our safety data sheet (SDS), which is available upon request.

# tesa<sup>®</sup> 60151 Adhesion Promoter Glass



제품 정보

## Disclaimer

테사에서 판매하는 제품들은 엄격한 품질관리를 통해 생산되고 있으며, 테사에서 제공하는 전문적인 정보들은 오랜기간의 경험을 기반으로 하고 있습니다. 관련 정보는 평균값에 근거하며, 특별한 용도에는 적합하지 않을 수 있습니다. tesa SE는 관련 정보의 명시적 또는 암묵적인 보증을 하는 것은 아니며, 이는 특별한 용도에 적합성 또는 상업성과 관련한 어떠한 암묵적인 보증도 포함하지 않습니다. 사용자는 제품을 사용하기 전에 적용부위에 적합한지를 검토하시기 바라며, 기타 문의 사항이 있으시면 저희 직원에게 문의 바랍니다



관련제품 최신자료는 다음의 경로를 클릭하세요  
<http://l.tesa.com/?ip=60151>