




# tesa<sup>®</sup> 69604

## Optically Clear Adhesive



### Product Information

100 µm UV-herdbar optisk klar limoverføringstape

### Produktbeskrivelse

tesa<sup>®</sup> 69604 er en svært transparent UV-herdbar limoverføringstape produsert under kontrollerte rene romforhold og designet for optisk klar laminering.

### Funksjoner

- Høy transmittans og lav uklarhet
- God spaltefylling
- Fremragende temperatur-, fukt- og UV-bestandighet\* Fremragende ITO-stabilitet (syrefri)
- Fremragende undertrykking av sent fremkommende bobler, selv i krevende miljøer
- Høy bindestyrke
- Glatt og enkel fjerning av dekkpapiret

### Applikasjon

- Optisk klar laminering mellom stive og stive eller fleksible og stive underlag
- Liming av skjermer med høye blekktrinns for å dekke glass eller berøringspanel

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Produktinnhold

- |                 |             |   |             |
|-----------------|-------------|---|-------------|
| • Bæremateriale | Ingen       | • Linerfarge                                  | Transparent |
| • Klebetype     | Akryl       | • Linertykkelse (lettavtagelig liner)         | 50 µm       |
| • Type liner    | PET-film    | • Linertykkelse (Vanskeligst avtagelig liner) | 75 µm       |
| • Farge         | Transparent | • Tapetykkelse                                | 100 µm      |

### Egenskaper / ytelsesverdier

- |                             |      |                              |       |
|-----------------------------|------|------------------------------|-------|
| • Aldringsbestandighet (UV) | good | • Haze                       | 0.2 % |
| • Brytningsindex            | 1.48 | • Klebeevne                  | good  |
| • Fuktbestandighet          | good | • Overføring (380 - 780nm) > | 99 %  |

### Klebekraft

- |                                    |           |                                  |          |
|------------------------------------|-----------|----------------------------------|----------|
| • Klebeevne på Glass (Umiddelbart) | 10.5 N/cm | • PC (after UV curing)           | 10 N/cm  |
| • Glass (after UV curing)          | 11.1 N/cm | • Klebeevne på PET (umiddelbart) | 8.6 N/cm |
| • Klebeevne på PC (umiddelbart)    | 9.8 N/cm  | • PET (after UV curing)          | 7.9 N/cm |

For latest information on this product please visit <http://l.tesa.com/?ip=69604>



# tesa<sup>®</sup> 69604

## Optically Clear Adhesive

### Product Information

#### Additional Information

50 µm lett avtakelig PET-dekkpapir (utenfor rullen)

Verdiene for klebekraft er målt med 50 µm PET-folie (se Teknisk informasjon)

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=69604>