

Product Information

Tynn 48 µm dobbeltklebende tape

tesa® 4972 er en tynn, klar, dobbeltklebende polyestertape med akrylkleber

- Kun 48µm tykk
- God klebeevne tross den lave tykkelse
- God håndtering ved utstansing

Main Application

- Montering av metall- og plastmerker og skilt
- Feste av refleksjonsfolie på LCD-rammer
- Skjøte av tynn plastfilm

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Technical Data

• Bæremateriale	PET-film	• Klebetype	tackified acrylic
• Farge	transparent	• Bruddforlengelse	50 %
• Total tykkelse	48 µm	• Bruddstyrke	20 N/cm

Adhesion to

• Klebeevne på Stål (umiddelbart)	7.0 N/cm	• Klebeevne på Stål (etter 14 dager)	9.6 N/cm
• Klebeevne på ABS (Umiddelbart)	5.3 N/cm	• Klebeevne på ABS (etter 14 dager)	6.5 N/cm
• Klebeevne på Aluminium (umiddelbart)	5.2 N/cm	• Klebeevne på Aluminium (etter 14 dager)	7.7 N/cm
• Klebeevne på PC (umiddelbart)	6.5 N/cm	• Klebeevne på PC (etter 14 dager)	8.6 N/cm
• Klebeevne på PE (umiddelbart)	3.1 N/cm	• Klebeevne på PE (etter 14 dager)	3.5 N/cm
• Klebeevne på PET (umiddelbart)	5.3 N/cm	• Klebeevne på PET (etter 14 dager)	7.0 N/cm
• Klebeevne på PP (Umiddelbart)	3.0 N/cm	• Klebeevne på PP (etter 14 dager)	4.8 N/cm
• Klebeevne på PS (umiddelbart)	5.4 N/cm	• Klebeevne på PS (etter 14 dager)	7.1 N/cm
• Klebeevne på PVC (umiddelbart)	5.7 N/cm	• Klebeevne på PVC (etter 14 dager)	9.4 N/cm

Properties

• Temperaturbestandighet (Korttids-)	200 °C	• Kjemikaliebestandig	●●●●
• Temperaturbestandighet (Langtids-)	100 °C	• Bestandig over for bløtgjørere	●●●●
• Klebeevne	●●	• Statisk strekkholdkraft ved 23°C	●●●●
• Aldringsbestandighet (UV)	●●●●	• Statisk strekkholdkraft ved 40°C	●●
• Fuktbestandighet	●●●●		

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

tesa® 4972

Product Information



Additional Information

Innleggsvarianter:

PV42 brunt glassinepapir (71µm; 82g/m²)

PV40 hvitt glassinepapir / rød tesa-logo (71µm; 82g/m²)

PV43 hvit PE-belagt papir / blå tesa®-logo (122µm; 120g/m²)

PV52 transparent PET-materiale (75µm; 110g/m²)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit
<http://l.tesa.com/?ip=04972>