



Product Information

48µm double sided black filmic tape

Product Description

tesa® 51972 is a double-sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

Product Features

- Thickness: 48µm
- High adhesion level
- · Excellent resistance to demanding environmental conditions
- Excellent handling performance in converting processes

Application Fields

- Mounting of metal or plastic badges and signs
- Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

BackingType of adhesive	PET film tackified acrylic		48 μm black		
Properties/Performance Values					
 Elongation at break Tensile strength Ageing resistance (UV) Chemical Resistance Humidity resistance 	50 % 20 N/cm very good good very good	 Static shear resistance at 40°C Tack 	good medium medium 100 °C		
Softener resistance	good	Temperature resistance short term	200 °C		



tesa® 51972

Product Information

Adhesion to Values

•	ABS (initial)	5.3 N/cm
•	ABS (after 14 days)	6.5 N/cm
•	Aluminium (initial)	5.2 N/cm
•	Aluminium (after 14 days)	7.7 N/cm
٠	PC (initial)	6.5 N/cm
٠	PC (after 14 days)	8.6 N/cm
٠	PE (initial)	3.1 N/cm
٠	PE (after 14 days)	3.5 N/cm
٠	PET (initial)	5.3 N/cm

• PP (initial) 3 N/cm • PP (after 14 days) 4.8 N/cm • PS (initial) 5.4 N/cm • PS (after 14 days) 7.1 N/cm • PVC (initial) 5.7 N/cm • PVC (after 14 days) 9.4 N/cm • Steel (initial) 7 N/cm • Steel (after 14 days) 9.6 N/cm

7 N/cm

• PET (after 14 days)

Additional Information

Liner variants: PV20 brown/blue logo glassine paper (71µm; 82g/m²)

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 22/02/24 – en-US