

# tesa® 50999

## **Product Information**



#### Heat Tabbing Film

## **Product Description**

tesa® 50999 is a co-extrusion PE/PET translucent heat weldable film, which ensures extremely high liner pick-up rates. These heat tabs are formed by using the right parameters of heat, pressure and time.

Recommended parameter set: 155°C stamp temperature at 1 bar for 1.5 seconds.

#### **Product Features**

• tesa® Heat Tabbing Film can be securely attached to silicone free liner.

## **Application Fields**

- Fast and reliable liner removal in production
- · Automatic process applied by robots

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

•	Backing	multilayer film	•	lotal thickness	150 μm
•	Type of adhesive	none	•	Color	translucent
•	Type of liner	none			

## **Properties/Performance Values**

Elongation at break
Tensile strength
40 N/cm

#### **Additional Information**

Standard dimensions:

50 m x 15 mm

50 m x 30 mm

100m x 1000mm



tesa® 50999

**Product Information** 

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

